



STUCCO ITALIANO SRL

Viale S. Agostino, 346/A - 36100 Vicenza - Italia
Tel. +39 347 2469500 e-mail: info@stuccoitaliano.it

Technical Data sheet

DOLOMIA

Fine natural mineral lime finish

Name	DOLOMIA	
Description	natural mineral lime base wall covering for high decorative finish on interior and exterior surfaces.	
Composition	aged, finely filtered slaked lime putty, special powdered marble granules sifted and powder from vulcanic stones elected according to granule size of 000 = mm. 0.0 ÷ 1,2, mica flakes, water and special additives (no more than 2,5% total in wet volume)	
Type of Surface to be Covered		
New	plaster	no priming necessary
	gypsum	one coat of Quartz Primer
	plasterboard	one coat of Quartz Primer
	medium density	one coat of Quartz Primer
Old	old plaster	one coat of Normal Primer
	distemper/fast-drying	brush down thoroughly and one coat of Normal Primer
	limewash	brush down thoroughly
	polished lime finish	sandpaper, brush down and one coat of Quartz Primer
	washable paint	one coat of Quartz Primer

Performance	excellent very high decorative effect good drying capacity excellent natural anti-mould and mildew very high adhesion to support good coating capacity excellent filler properties excellent workability	
Appearance	It is a white paste which can be worked in rough o smooth finish. It is a very hard plaster once dry.	
Colours	white, but any colour colour possible from our chart of Colouring System	
Packaging	24 kg. net	polyethylene containers
Packaging	16 kg. net	polyethylene containers

TECHNICAL DATA

Application	by hand, with a steel trowel and brush trowel	
Dilution	none: ready-to-use paste	
Consumption	3,800 kg/sq.m.	
Drying (carbonation)	4 hours at 20°C 48 hours at 20°C 180 days	to the touch below the surface stable
Application Temperatures	min. 5 max 30°C - U.R. < 85 % ca.	
Specific weight	1,590 ± 50 (gr/LT.)	
Volumetric Mass	1,690 ± 60	
Viscosity	200,000 ± 25,000 CPS = 20° C (white)	
Fade resistance	resistant/non-resistant	(ASTM norms)
pH after 30 days	12.4 ± 0,20	
Vapour resistance	μ 24 ± 2 average	(ASTM norms)
Vapour permeability	gr/m2 x 24 h = 260 ± 30 (ASTM norms)	
Inflammability	non-flammable	
VOC Classification	As per Dir. 2004/ 427 EC, Cat . A/c: Paints for exterior walls of mineral substrate. Eu limit 75 g/l (2007) 40 g/l (2010). This product contains 0 g/l of Voc.	
Shelf Life	48 months	
Storage Suggestions	Product maintains its characteristics best if protected from extreme heat or cold. Avoid freeze.	
Safety Norms	Lime products are caustic. In case of contact with eyes or skin, rinse thoroughly with water. Keep out of reach of children.	
Disposal	Product must be disposed of according to norms and regulations in force. Containers must be sent for recycling.	

We have drawn up the material presented above to the best of our technical and experiential knowledge. Nevertheless, our suggestions and recommendations are not guaranteed. We reserve the right to make modifications to the present information without previous warning.