

STUCCO ITALIANO SRL

Via dell'Artigianato 7, Sarcedo 36030 - Italia Tel. +39 347 2469500 e-mail: info@stuccoitaliano.it

Specification Sheet

LIBERTY EPOQUE

Name LIBERTY EPOQUE SILVER AND GOLD

Description This highly decorative, breathable finish is for interior walls. Because of the precious metals contained in the pigment, it takes on the appearance of velvet or suede.

Composition Water soluble resins and metallic pigments.

Application fields All wall surfaces and interior furnishings.

ColourSILVER that is white which can be tinted any colour from light to dark.GOLD that is yellowish color and can be tinted to get different gold tint and
bronze effect

Dilution The dilution depends on the kind of finish. It's ready to use for most applications and can be diluted up to 100%.

Appearance Gel.

Yield Its yield varies a lot depending on the kind of finish. Three metres to the litre for a suede finish, 35 sq. m. when diluted and applied with a sea sponge.

Tools nedeed	Metal trowels, rags, decorative rollers and marine sponges.
Temperature for application	Between 5 and 36° C with a humidity of less than 85%.
Drying time	To the touch – 2 hours at 20° C with humidity $<$ 70%. Completely - 48 hours at 20° C with humidity $<$ 70%.
Packaging	Plastic tubs – 1 and 5 litres.
Storage	24 months if protected from freezing.

Yield	Depends on the finish: from 40 to 5 sq.metre/liter
Safety measures	Do not swallow. Avoid contact with eyes. Keep out of reach of children.
Disposal	Containers recyclable. Dispose of according to the laws in your area.
Voc Classification:	Cat. A/I finishes for decorative effects. EU limit: 300g/l of VOC. This product contains 0 g/l of VOC
Specific weight:	1.14 kg / 1
рН	7.5 ± 0.2
Vapour Permeability	0.24 m. (max comsemted limit: 2 m., DIM 52 615)

FINISH POSSIBLE: Brocade, Satin lamé, Sea Sponge, With brush

For application see the videos of application since they are various and very different one to the other.

The technical information and application advice given are based on the present state of our best scientific and practical knowledge, nevertheless the suggestions and advice are provided without warranty.

The company reserves the right to make modifications at any time.

Page 2