



STUCCO ITALIANO srl

Via dell'Economia, 117- 36100 Vicenza (Vi) - Italia
e-mail: info@stuccoitaliano.it / polistena@stuccoitaliano.it Skype: stucco.italiano
C.F. / P.Iva 03744780242 REA 350312
IBAN IT30G050341180000000000847 BIC-Swift BAPPIT21127

TECHNICAL DATA SHEET

OSSIDATO DARK

Ossidato Dark is a decorative water-based decorative paint, with an antique effect. Its main features are the ease and speed of application and the fact that it's highly decorative and washable.

It has a primer and additives to obtain pleasant shiny metallic silver or gold effects.

It can be applied on all building surfaces provided they have a smooth finish.

It has excellent resistance to the effects of light, knocks and abrasions. It resists molds and bacteria and with its anti-static properties, repels dust. For this reason, it is particularly recommended for use in prestigious shops, elegant flats, professional studios and in places where there is wear and tear such as banks, offices, public and commercial buildings, kitchens, living rooms, etc.

Application	by hand, with brush or spalter, and trowel. In one or two coats
Dilution	Ready to use. For special finishes dilute it max.10%.
Yield	5-8 sq. m per liter/ layer
Drying	4 hours at 20°C to the touch 24 hours at 20°C below the surface
Application Temperatures	min. 8 - max 30°C - U.R. < 85 % ca.
Specific weight	1,040 ± 40 (gr/LT.)
Inflammability	non-flammable
VOC Classification	As per Dir. 2004/ 427 EC, Cat . A/c: Paints for exterior walls of mineral substrate. Eu limit 75 g/l (2007) 40 g/l (2010). This product contains 10 g/l of Voc.
Resistance to washing UNI 10560	> 5000 brush strokes
Classification EN 13300	Highly resistant to washing - Class 2
Shelf Life	18 months in original packaging.
Packaging	1 L. and 5 L. buckets.
Storage Suggestions	Product maintains its characteristics best if protected from extreme heat or cold. Avoid freezing.
Safety Norms	In case of contact with eyes rinse thoroughly with water. Keep out of reach of children.
Disposal	Product must be disposed of according to norms and regulations in force. Containers should be recycled.



STUCCO ITALIANO srl

Via dell'Economia, 117- 36100 Vicenza (Vi) - Italia
e-mail: info@stuccoitaliano.it / polistena@stuccoitaliano.it Skype: [stucco.italiano](https://www.skype.com/name/stucco.italiano)
C.F. / P.Iva 03744780242 REA 350312
IBAN IT30G050341180000000000847 BIC-Swift BAPPIT21127

Wall Preparation

New Walls

Make sure they are perfectly smooth or smooth and plaster them with enough material. Apply a coat of Normal Primer diluted with water 1 to 8 and after 4 hours apply Primer for Ossidato Dark with a brush or roller, taking care not to leave any marks typical of these tools (brush strokes or "orange peel" roller marks.) And allow it to dry completely.

Walls with old paint

Remove all old, unstable paint and apply a coat of Normal Primer diluted 1 to 8-10 with water. Smooth it out with fine stucco to obtain a smooth, uniform surface. Apply a coat of Normal Primer diluted 1 to 8 and after at least four hours apply Primer for Ossidato Dark. Allow it to dry completely.

Primer for Ossidato Dark comes in 2-liter containers.

Application

WARNING: It is necessary to check the compatibility of the colorants before use if they are different from those supplied by us.

After inserting the dye into the product, stir slowly, avoiding violent cutting movements. If using orbital mixers, use the minimum speed allowed by the appliance for 2 minutes.

Application with brush and spatula

Apply with a brush (or spalter). Immerse the brush directly into the material and apply it to one spot on the wall and from that spot, using short (8-14 cm) brush-strokes, move it in all directions.

Continue to repeat the same operation until you reach the end of the wall, taking care to cover the entire surface, but leaving more material in some areas and less in other areas.

As soon as the product begins to dry (after 18-20 minutes), it can be gone over with the appropriate flexible plastic spatula, exerting light pressure.

After 5 or 6 hours (at 20 ° C), you can repeat the operation. And after applying the product again, wait about 60 minutes, then go over it with the appropriate plastic or flexible steel spatula moving in all directions with long movements of about 18-20 cm., compressing the colored particles.

Brush application

Apply by brush or spalter. Immerse the brush directly into the material and apply it to one place on the wall and from there, use short (8-14 cm) brush-strokes, moving it in all directions. Continue repeating the same operation until the wall ends, taking care to cover the entire surface, but leaving more material in some areas and less in others. After 5 or 6 hours (at 20° C), you can repeat the operation and after applying the product wait for about 60 minutes. Then with a dry brush, go over



STUCCO ITALIANO srl

Via dell'Economia, 117- 36100 Vicenza (Vi) - Italia
e-mail: info@stuccoitaliano.it / polistena@stuccoitaliano.it Skype: [stucco.italiano](https://www.skype.com/name/stucco.italiano)
C.F. / P.Iva 03744780242 REA 350312
IBAN IT30G050341180000000000847 BIC-Swift BAPPIT21127

the entire surface moving in all directions with long movements of about 18-20 cm, compressing the colored particles slightly.

Application by trowel

Apply with a small, metal trowel using 20-30 cm strokes, crisscrossing in all directions. After 5 or 6 hours, repeat the operation and after about 60 minutes, when the drying is about to begin, compress the surface with a metal or light, plastic spatula making strokes in all directions, compressing the small colored particles.

Wash the tools with water

Metallic effect

Add a package of Metallic Additive for Ossidato (Silver or Gold) from l. 0.5 to a box of l.5,0 of Ossidato Dark

Application and possible coloring are as described above.