TECHNICAL DATA SHEET

-

MOTHER OF PEARL

Crushed Shell grinded and dryed of above 300°C for decorative use as additive for Marmrorino, Stucco Lava, Pastellone and other Stucco Italiano Plasters .

It gives shyne dots effect that comes from the inner part of the shell but also it adds small spot of brown and yellow colors coming from the other side of the shell granule.

Mother of Pearl comes in three dimensions:

Fine	400 to $800\;\mu m$	Marmorino Medium
Medium	800 to 1200 μm	Marmorino Medium, Marmorino Coarse, Stucco Lava, Pastellone
Coarse	1200 to 1800 μm	Dilavato

This additive has to be added to the plaster in a quantity proper to get the desidered effect. The packaging of grams 950 reflects our taste and the more common quantity for a 20-24 kg bucket of Marmorino, Stucco Lava or a 16 kg bucket of Pastellone.

Mix it to the material. It has not to be added in the first coat but in the secon and third for Marmorino and Pastellone and in the last one for Dilavato.

In Stucco Lava it depends on the desidered effect, usually it is added to the last two coats.

Note: this additive doesn't change the color and doesn't not affect the final hardness.